


PRESERV A - WN

'PRESERV A - WN' is a Non - Fluoro based, UV and weather stable White Backsheet. PRESERV A - 190 WN, 150 WN, 125 WN, 100 WN can be used for all Crystalline and many Thin - Film PV modules.

'PRESERV A - 275 WN' is suitable for PV modules with 1500V system voltage. The extremely low moisture permeability of this Backsheet makes it highly suitable for PV modules meant for tropical climatic conditions.

STRUCTURE



PROPERTIES - PRESERV A - 190 WN, 150 WN, 125 WN, 100 WN

Particulars	Test Method	Unit	Description	190 WN	150 WN	125 WN	100 WN
Thickness	Micrometre	µm		360	320	300	270
Width	Scale	mm		Up to 1310	Up to 1310	Up to 1310	Up to 1310
Tensile Strength @ max load	ASTM D 882	MPa	MD TD	≥90 ≥90	≥90 ≥90	≥90 ≥90	≥90 ≥90
Elongation @ break	ASTM D 882	%	MD TD	≥90 ≥90	≥90 ≥90	≥90 ≥90	≥90 ≥90
Thermal Shrinkage @ 150°C, 30 min.	ASTM D 1204	%	MD TD	≤1.5 ≤0.5	≤1.5 ≤0.5	≤1.5 ≤0.5	≤1.5 ≤0.5
Interlayer Adhesion Strength	ASTM D 903	N/cm	HPET/PET PET/PRIMER	≥5 ≥5	≥5 ≥5	≥5 ≥5	≥5 ≥5
Adhesion Strength with Encapsulant	ASTM D 903	N/cm	Backsheet/ EVA	≥70	≥70	≥70	≥70
Moisture Barrier - MVTR @ 38°C, 90% RH	ASTM F 1249	g/ (m ² - day)		≤ 1.4	≤ 1.5	≤ 1.6	≤ 1.7
Dielectric Strength	ASTM D 149	kV		23	20	20	18
System Voltage	IEC 61730 - 1	VDC		≥1000	≥1000	≥1000	≥1000

Width: Up to 1000 mm - all sizes available. Sizes >1000 mm - make to order

PROPERTIES - PRESERV A - 275 WN

Particulars	Test Method	Unit	Description	275 WN
Thickness	Micrometre	µm		365
Width	Scale	mm		Up to 1310
Tensile Strength @ max load	ASTM D 882	MPa	MD TD	≥ 90 ≥ 90
Elongation @ break	ASTM D 883	%	MD TD	≥ 90 ≥ 90
Heat Shrinkage @ 150°C, 30 min.	ASTM D 1204	%	MD TD	≤ 1.5 ≤ 0.5
Interlayer Adhesion Strength	ASTM D 903	N/cm	HPET/PET PET/PRIMER	≥ 5 ≥ 5
Adhesion Strength with Encapsulant	ASTM D 903	N/cm	Backsheet / EVA	≥ 100
Moisture Barrier - MVTR @ 38°C, 98% RH	ASTM F 1249	g/(m ² - day)		≤ 1.6
System Voltage	IEC 61730 - 1	VDC		1500
Total Thickness of Layers @ relied upon insulation	Micrometre	µm		≥ 300

Width: Up to 1000 mm - all sizes available. Sizes >1000 mm - make to order

PRESERV A - WN



Packing Unless specified, below is the standard packing of 'PRESERV'
Length/Roll: 180 or 230 metres | # No. of Rolls/Pallet: 9
Total Linear Metres/Pallet: 1620 or 2070
Each roll is wrapped with polyethylene sheet
Rolls are palletize vertically placed with top and bottom lid

Note : The above technical information represents the typical range of properties and is believed to be correct as on date. However, this data should not be used to establish specification limits or used as basis for design. Lamination parameters and Quality of other components of the laminate during module manufacturing impact on the overall performance of the module, and hence we recommend the user to carry out intensive trials to test suitability of this product and module laminating conditions. RenewSys gives no warranty and assumes no liability on connection with any use of this information and is subject to the RenewSys general terms and conditions.

inter
**solar
award**

2018
Finalist

CONSERV®
E 360 - POE
Encapsulant

A - WN - 07/2021/1